

OFFICE OF NAVAL RESEARCH

CONTRACT N5ori-076

T. O. 54

Nr-330-025

AD No. 17 236
ASTIA FILE COPY
"CHARACTERIZATION OF CELLULOSE AND POLYPEPTIDE POLYMERS"

Paul Doty

Technical Report No. 2

"MOLECULAR DIMENSIONS OF CELLULOSE DERIVATIVES"

Paul Doty, Nathaniel S. Schneider, and Alfred Holtzer

Gibbs Memorial Laboratory

Harvard University

Cambridge, Massachusetts

August 7, 1953

MOLECULAR DIMENSIONS OF CELLULOSE DERIVATIVES^{*,1}

Paul Doty, Nathaniel S. Schneider, and Alfred Holtzer

Gibbs Memorial Laboratory, Harvard University, Cambridge, Mass.

* Appeared as a Letter-to-the-Editor, J.A.C.S. 75, 754 (1953)

Although it has been widely believed that the molecules of cellulose derivatives are considerably more extended than typical vinyl polymers, the direct evidence supporting this is principally that of early light scattering measurements², the accuracy of which might be in doubt due to the colloidal contaminants which are difficult to remove. We report here current work on the angular distribution of scattered light from sodium carboxymethyl cellulose (unfractionated, 1.15 Acid groups per glucose), NaCMC, and cellulose trinitrate (fractionated), CN, which define more precisely the extent of coiling in these derivatives and demonstrate the inapplicability of the Flory-Fox³ relation to cellulose derivatives of low and moderate molecular weight.

The customary interpretation of Zimm plots of the scattering data for NaCMC showed its weight average molecular weight to be 430,000 and its z-average end-to-end length to be 2410, 2590, and 3100 Å. in 0.5, 0.05, and 0.01 N NaCl solutions respectively. The corresponding intrinsic viscosities were 7.03, 10.1, and 15.9. These sizes are to be compared with the contour length which is estimated to be 5280 Å. on the assumption that the z-average molecular weight is 1.5 times the weight average one. Hence the mean length of these chains is about half their contour length. Since the Gaussian distribution of segments is no longer a good approximation

for chains with valence angle near 110° when the mean length is more than one-third the contour length⁴, we are clearly dealing with non-Gaussian chains.

This fact has implications in both light scattering and intrinsic viscosity interpretations. In the former it means that the radius of gyration and not the mean length should be evaluated from the data since it is only the radius that can unambiguously be determined. The mean length is equal to $\sqrt{6}$ times the radius for Gaussian coils but the proportionality constant increases to $\sqrt{12}$ as a rod-like configuration is approached. Consequently, the sizes listed above are the radii of gyration divided by $\sqrt{6}$. It is of interest to note that the reciprocal intensity versus $\sin^2 \theta/2$ plot has a pronounced downward curvature as would be expected for chains deviating from Gaussian behavior. Consequently, the use of dissymmetry measurements leads to dimensions that are too small.

With respect to intrinsic viscosity, it is clear that non-Gaussian chains of this type cannot possibly satisfy the premise of the Flory-Fox relation, that is that the effective hydrodynamic volume of the polymer molecule is spherical and can be characterized by a radius that varies directly with a linear parameter of the Gaussian distribution. This is borne out by the constant ϕ of the Flory-Fox relation calculated from the mean lengths and intrinsic viscosities given above and the z-average molecular weight. It is found to have values of about 0.31×10^{21} in contrast to 2.1×10^{21} for Gaussian coiled polymers. The use of the latter value implies that the unusually large temperature dependence of the viscosity observed in cellulose derivatives results solely from changes in dimensions. When the chains are non-Gaussian, however, the temperature

dependence of ϕ tends to mask these dimensional changes. Consequently, the dimensions of cellulose derivatives cannot be determined from viscosity measurements except within the region of high molecular weight or high temperature where the configurations are Gaussian. The neglect of these considerations has led to the erroneous conclusion that cellulose derivatives at ordinary temperatures are as flexible as typical vinyl polymers⁵.

As an example of Gaussian behavior possible in cellulose derivatives of high molecular weight, we report measurements on one CN fraction in acetone which was found to have a molecular weight of 2.5 million and a mean length of 4070 Å. The ratio of this to the contour length is 1:10. Assuming that the mean end-to-end length is proportional to the square root of the molecular weight, we find that the transition from Gaussian to non-Gaussian character occurs at a molecular weight of about 130,000 for CN. Of course, the transition occurs at a higher molecular weight for NaCMC since it is somewhat more extended. In the CN fraction mentioned the intrinsic viscosity calculated from the Flory-Fox relation with correction for polydispersity is 28.5 which compares favorably with 31.5 obtained from extrapolating measured values to zero gradient.

1. This work was carried out under ONR Contract N5ori-07654, NR-330-025.
2. (a) R. S. Stein and P. M. Doty, J.A.C.S. 68, 159 (1946);
(b) R. M. Gadger and R. H. Blaker, J. Phys. Colloid Chem. 53, 1051 (1949)
3. P. J. Flory and T. G. Fox, J.A.C.S. 73, 1904 (1951)
4. L. R. G. Treloar, Proc. Phys. Soc. 55, 345 (1943)
5. L. Mandelkern and P. J. Flory, J.A.C.S. 74, 2522 (1952); see also S. Nouman and P. J. Flory, J. Polymer Sci. 10, 121 (1953)